



GB98/03636

The
Patent
Office

PCT/GB 98/03636
09/555544

INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP9 1RH

REC'D 01 FEB 1999

WIPO

PCT

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.


Signed

Dated

Andrew Gernsey

114 DEC 1998





Patents Form 1/77
(D-1)



Request for a grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office
Cardiff Road
Newport
Gwent NP9 1RH
0506097 3322907-1 002246
001/7700 25.00 - 7705578.4

1.	Your reference	P/3952.GB JAT		
2.	Patent application number (The Patent Office will fill in this part)	9725878.4		- 5 DEC 1997
3.	Full name, address and postcode of the or of each applicant (underline all surnames)	IMPERIAL COLLEGE OF SCIENCE, TECHNOLOGY & MEDICINE Sherfield Building Exhibition Road London SW7 2AZ Patents ADP number (if you know it) 580 8068 001 If the applicant is a corporate body, give the country/state of its incorporation United Kingdom		
4.	Title of the invention	VAPOUR DEPOSITION		
5.	Name of your agent (if you have one)	D YOUNG & CO		
	"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	21 NEW FETTER LANE LONDON EC4A 1DA Patents ADP number (if you have one) 59006		
6.	If you are declaring priority from one or more earlier patent applications, give the country and date of filing of the or each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of filing (day/month/year)
7.	If this application is divided or otherwise derived from an earlier UK application, give the number and filing date of the earlier application	Number of earlier application	Date of filing (day/month/year)	

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:
a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or
c) any named applicant is a corporate body.
See note (d))

YES

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form NONE

Description 3

Claims(s) 0

Abstract 0

Drawing(s) 0

10. If you are also filing any of the following, state how many against each item.

Priority documents NONE

Translations of priority documents NONE

Statement of inventorship and right to grant of a patent (Patents Form 7/77) NONE

Request for preliminary examination and search (Patents Form 9/77) NONE

Request for substantive examination (Patents Form 10/77) NONE

Any other documents (please specify) NONE

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date

D Young & Co

D YOUNG & CO

05 12 97

Agents for the Applicants

12. Name and daytime telephone number of the person to contact in the United Kingdom

J A TURNER

01703 634816

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 01645 500505
- Write your answers in capital letters using black ink or you may type them
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Novel Processing Technique: Electrostatic and Flame Assisted Vapour Deposition

K. L. Choy

Department of Materials, Imperial College of Science, Technology and Medicine, Prince Consort Road, London SW7 2BP

J. T. H. Chang

School of Metallurgy and Materials, Birmingham University, Edgbaston, Birmingham, B15 2TT

ABSTRACT

A novel and cost-effective vapour synthesis technique called *Electrostatic and flame assisted vapour deposition (EFAVD)* has been developed to deposit ceramic films and coatings in an open atmosphere. This technique combines the advantages of flame synthesis (FS), electrostatic spray deposition, chemical vapour deposition (CVD) and sol-gel techniques. In addition, this method can also be adapted for the production of ultrafine powders and near shape engineering parts.

INTRODUCTION

The applications of ceramics as structural coatings and functional electronic films are widespread and expanding rapidly. There are needs for improved methods of fabrication for ceramic films and coatings. Various conventional and commercial techniques such as CVD, physical vapour deposition (PVD), flame spraying deposition (FSD), combustion chemical vapour deposition (CCVD), and sol-gel have been investigated.

Both CVD and PVD involve the use of sophisticated and expensive deposition chamber and/or vacuum system. Applications of CVD/PVD methods to ceramic films are limited to the coating process in which the required film thickness and coating area are relatively small. In addition, CVD often leads to difficulties in controlling the stoichiometry of multicomponent oxide films and problem arise due to differences in vapour pressure of CVD reagents and low growth rate of deposited films. PVD method such as the radio frequency sputtering gives low deposition rates and low yield. Reactive magnetic sputtering and ion-beam sputtering both need expensive equipment and highly skilled technician. Conventional evaporation method has difficulties in depositing materials with high melting/vaporising temperatures, except the very expensive electron beam evaporation (EB-PVD) method. Moreover, EB-PVD has difficulties in controlling the stoichiometry of multicomponent oxide films.

FSD [1] produces films with morphology, microstructure and electrical properties dependent on temperature of substrate, coating concentration, carrier gas flow etc. It is therefore complex to control the variables and difficult to implement.

CCVD [2] has a low deposition rate and experiences difficulties in depositing dense thick film (>10 microns). Moreover, it involves the use of high flame temperature (>800°C), cause premature decomposition and the loss of some precursors to the surrounding.

For the production of ceramic film, sol-gel has two problems; the films tend to crack and the film has to have a definite thickness. These are major obstacles to utilization.

Similarly, there is a lack of processing methods that can produce ultrafine powders cost effectively. Materials with nanostructured have been recognised to exhibit attractive mechanical, electrical, optical and magnetic properties which are not observed in materials with coarse-grained structures. Nanostructured powders can be synthesized by chemical, physical and mechanical methods. Gas condensation in vacuum is the most applicable method for the synthesis of high purity ceramic nanopowders with well controlled particle size and distribution. However, such processing method is very expensive. Thus, limit the applications of ultrafine powders in high value added components.

THE INVENTION

page 2

Electrostatic and flame assisted vapour deposition (EFAVD) of films and coatings

EFAVD is a novel and cost-effective coating method which involves spraying atomised precursor droplets into a flame, within an electric field between the source and the substrate, where the charged aerosol undergo combustion and/or chemical reactions in the vapour phase near the vicinity of the substrate. This results in the formation of a stable solid film with excellent adhesion onto a substrate.

The electric field will charge the droplets and electrostatically attract the droplets from the outlet towards the substrate. In addition, an electric field and/or magnetic field could be created across the flame axis to steer and/or focus the stream of fine droplets in transit from the outlet to the substrate.

This technique combines the features and advantages of flame synthesis (FS), electrostatic assisted vapour deposition [3], chemical vapour deposition (CVD) and sol-gel techniques.

Key advantages of EFAVD include:

- simple/flexible/mobile equipment
- low cost, safe process using sol precursors and/or water based precursors
- relative low flame/deposition temperature for crystalline (e.g. 550-800°C for Y2O3-ZrO2)
- thin and thick film can be produced
- dense and porous film can be deposited onto dense or porous substrates. The deposition of dense film onto porous substrates involves the deposition of an amorphous interlayer).
- the choice of precursor is important. For the deposition of dense film, the precursor is based on sol precursor. The deposition of porous films can be based on sol or water soluble precursors.
- low consumption of precursor (e.g. 1 ml 0.05M to produce 1 micron thick film on 1cm x 1 cm substrate).
- high deposition rate
- substrate may be simple or complex in shape and may be ceramic or metal
- the process could be scale-up for large scale/large area production.
- single production process without the need for further heat treatment.
- simple, multicomponent oxides and doped oxides can be manufactured with well controlled structure in an open-atmosphere
- non oxides such as sulfides, carbides, etc. can be produced in a controlled atmosphere
- minimum loss of precursor to the surrounding as the electric field directs the charged aerosol precursors to the substrate/object forming table/powder collector
- by using sol precursor and incorporating gas condensation technique into the EFAVD, ultrafine

powders (in nanometer range) can be produced and collected in a cold collector (with a different polarity/potential than the source)

- by incorporating movable object forming table controlled by a computer aided design model (CAD) into the EFAVD, a 3-D object can be constructed layer by layer.

Process principle of the EFAVD for rapid prototyping

Atomised and charged precursor droplets are sprayed across an electric field in a flame source, where the charged aerosol undergo combustion and/or chemical reactions in the vapour phase near the object forming table to produce a 2D cross-sectional layer of the ceramic component. A dense 3D ceramic component is then constructed layer and layer with the required fine details. The movement of the table and hence the shape of the object is controlled by the CAD.

It is also possible to move the flame source using a computer controlled CAD system.

Such direct rapid prototyping using flame source for the formation of the required material would be cheaper than those using laser source.

REFERENCES

- [1] Choy, K. L., "Flame Assisted Vapour Deposition of Ceramic Films and Coatings", British Ceramic Proceedings, The Institute of Materials (1995) 65-74.
- [2] Hunt, A. T., W. B. Carter, and Cochranm J. K., Applied Physics, 63 (1993), No. 2, 266-268.
- [3] Choy, K. L., and Bai, W., "A method of depositing Ceramic Films and Coatings", International PCT Application No. PCT/GB96/03105.

PCT CB 98103636

D Young & Co

7.12.98